

[www.stahl.com](http://www.stahl.com)

The information provided herein is not intended to form part of any offer or contract for the sale. Pictures, descriptions and statements are only artistic impressions and they are not representations of fact. STAHL does not warrant the accuracy and correctness of the information and will not be responsible in any way for any inaccuracy or omission of information herein, as well as for changes in colors and printing errors, or for any loss suffered by any person as a result of relying on the information.

# We imagine leather finishing pigments with exceptional performance

If it can be imagined,  
it can be created

# The high performance solution for leather finishing

Neosan® 2000 pigments series

The Neosan® 2000 range offers a broad color palette of shades in aqueous, casein free pigment dispersions. Very finely dispersed and highly concentrated, these pigments have been developed for high performance leather finishes. The Neosan® 2000 pigments series has high covering power and offer outstanding, innovative advantages for all kinds of leathers.

| Product                  | Pigment Type     | Solids (%) | PVC Migration IUF 442** | Lightfastness ISO-105-B02* |                    | Fakra ISO-105-B06 - DIN 75 202* |                    | Heat Yellowing 144hrs @100°C** |                    |
|--------------------------|------------------|------------|-------------------------|----------------------------|--------------------|---------------------------------|--------------------|--------------------------------|--------------------|
|                          |                  |            | Full Shade              | Full Shade                 | Reduced Shade 1:10 | Full Shade                      | Reduced Shade 1:10 | Full Shade                     | Reduced Shade 1:10 |
| Neosan® 2000 White       | TiO <sub>2</sub> | 46.0       | -                       | 8                          | -                  | 8                               | -                  | 4                              | -                  |
| Neosan® 2000 White HC    | TiO <sub>2</sub> | 63.0       | -                       | 8                          | -                  | 8                               | -                  | 4                              | -                  |
| Neosan® 2000 Citron      | Organic          | 16.0       | 5                       | 8                          | 8                  | 8                               | 8                  | 5                              | 5                  |
| Neosan® 2000 Yellow      | Organic          | 20.0       | 5                       | 8                          | 8                  | 8                               | 8                  | 5                              | 4-5                |
| Neosan® 2000 Orange      | Organic          | 21.0       | 5                       | 8                          | 8                  | 8                               | 8                  | 5                              | 5                  |
| Neosan® 2000 Red Brown   | Iron Oxide       | 50.0       | 5                       | 8                          | 8                  | 8                               | 8                  | 5                              | 5                  |
| Neosan® 2000 Light Brown | Iron Oxide       | 50.0       | 5                       | 8                          | 8                  | 8                               | 8                  | 5                              | 5                  |
| Neosan® 2000 Bordeaux    | Organic          | 24.0       | 4-5                     | 8                          | 8                  | 8                               | 8                  | 5                              | 5                  |
| Neosan® 2000 Magenta     | Organic          | 16.0       | 5                       | 8                          | 8                  | 8                               | 8                  | 4                              | 4-5                |
| Neosan® 2000 Cherry Red  | Organic          | 23.0       | 5                       | 8                          | 8                  | 8                               | 8                  | 5                              | 5                  |
| Neosan® 2000 Beige       | Iron Oxide       | 40.0       | 5                       | 8                          | 8                  | 8                               | 8                  | 5                              | 5                  |
| Neosan® 2000 Dark Brown  | Inorganic        | 47.0       | 5                       | 8                          | 8                  | 8                               | 8                  | 5                              | 5                  |
| Neosan® 2000 Violet      | Organic          | 26.0       | 5                       | 8                          | 8                  | 8                               | 8                  | 5                              | 4-5                |
| Neosan® 2000 Blue        | Organic          | 22.0       | 5                       | 8                          | 8                  | 8                               | 8                  | 4-5                            | 4-5                |
| Neosan® 2000 Green       | Organic          | 24.0       | 5                       | 8                          | 8                  | 8                               | 8                  | 4                              | 4-5                |
| Neosan® 2000 Black       | Inorganic        | 30.0       | 5                       | 8                          | 8                  | 8                               | 8                  | 5                              | 5                  |
| Neosan® 2000 Deep Black  | Inorganic        | 18.0       | 5                       | 8                          | 8                  | 8                               | 8                  | 5                              | 5                  |

\* Wool Blue Scale    \*\* Grey Scale    Reduced Shade 1:10 with White Pigment

